

PLEXIGLAS® 7N

Product Profile:

PLEXIGLAS® 7N is an amorphous thermoplastic molding compound (PMMA).

Typical properties of PLEXIGLAS® molding compounds are:

- good flow
- high mechanical strength, surface hardness and mar resistance
- high light transmission
- very good weather resistance
- free colorability due to crystal clarity.

Special properties of PLEXIGLAS® 7N molding compound are:

- very good mechanical properties
- high heat deflection temperature
- very good flow / melt viscosity
- AMECA listing.

Application:

Used for injection molding optical and technical items.

Examples:

optical waveguides, luminaire covers, automotive lighting, instrument cluster covers, optical lenses, displays, etc.

Processing:

PLEXIGLAS® 7N can be processed on injection molding machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.

For more information:



VAMP-TECH S.p.A
Via delle Industrie 10/12 - 20874 Busnago (MB)
Phone +39.039.6957821
Fax: +39.039.6820563-6956388
E-mail: marketing@vamptech.it

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® 7N
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3200
Stress @ Break	5 mm/min	MPa	ISO 527	73
Strain @ Break	5 mm/min	%	ISO 527	3.5
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	103
Glass Transition Temperature		°C	ISO 11357	110
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	100
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	95
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	8
Fire Rating			DIN 4102	B2
Flammability UL 94	1.6 mm	Class	IEC 707	HB
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	6
Optical Properties				
Luminous transmittance	d=3 mm	%	ISO 13468-2	92
Haze			ASTM D1003	< 0.5
Refractive Index			ISO 489	1.49
Other Properties				
Density		g/cm ³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		max. 93
Predrying Time in Desiccant-Type Drier		h		2 – 3
Melt Temperature		°C		220 – 260
Mold Temperature (Injection Molding)		°C		60 – 90

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. Evonik Industries is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.
® = registered trademark
PLEXIGLAS and PLEXIMID are registered trademarks of Evonik Röhm GmbH.

Evonik Industries AG Kirschenallee 64293 Darmstadt
Telefon +49 6151 18-4711 Telefax +49 6151 18-3177
www.plexiglas-polymers.com

Ref. No.: MC105-E3 V0160 Date: 2013-02-05
